

Technical Datasheet

09.12.2020


TERRAWET Matt Coating G 9/131 silk matt-040

1 / 2

Product description

Water-based semi-matt coating with fast drying and a very high wet block resistance.

Properties



Gloss	■ ■ ■ ■ □ □ □ □ □ □
Scuff resistance	■ ■ ■ ■ ■ ■ ■ ■ □ □
Hot foil stamping	■ ■ ■ ■ ■ ■ ■ ■ □ □
Crackling tolerance	■ ■ ■ ■ ■ ■ ■ ■ □ □
Foaming tolerance	■ ■ ■ ■ ■ ■ ■ ■ □
Drying	■ ■ ■ ■ ■ ■ ■ ■ □ □
Two-sided coating	■ ■ ■ ■ ■ ■ ■ ■ □
Wet block resistance	■ ■ ■ ■ ■ ■ ■ ■ ■ ■
UV varnishing	■ ■ ■ ■ ■ ■ ■ ■ □ □
Counter glueing	■ ■ ■ ■ ■ ■ ■ ■ □ □
Slip angle	20° -24°
Foil lamination	■ ■ ■ ■ ■ □ □ □ □ □
Heat resistance	up to 120°C

Material characteristics

- Viscosity: 40 sec. (20°C, DIN 4 mm cup)
- Viscosity: 60 sec. (20°C, DIN 4 mm cup)

Application (End Uses)

- Wet glue (Other non-food, Beverages)
- Commercials (Brochures)
- Folded boxes (Other non-food, Food indirect, Dry foodstuff packagings)
- Corrugated (Displays)

Processes

- Wet-in-wet
- Sheet-fed offset, coating unit (chambered doctor blade or roller system)

Substrate

- Reversible PE coated board
- Coated paper
- Coated board

Legislation assessment

- In principal the product can be used as directed and with a complete drying for the coating of foodstuff packagings for the indirect contact to the filling good. For information about the food legislation assessment of this product (e. g. demands on the Nestlé "Guidance Note on Packaging Inks" and the Swiss Ordinance (SR 817.023.21 - ordinance of the Swiss Confederation on materials & articles in contact with food)) we ask you to contact our department for quality, environment and product safety. T: +49 (0) 5132 5009-140 mail to: QUM.ACTEGA.Terra @altana.com

Processing recommendations

- Stir well before use!
Mechanical stirring is recommended.
- Recommended coating application: 3,5 - 5 g/m²/wet
- Please use printing inks/foil inks suitable for coating.
- Resistance against alkali, alcohol

Technical Datasheet

09.12.2020

TERRAWET Matt Coating G 9/131 silk matt-040

2 / 2

and solvents should be given according to DIN ISO 2836, formerly DIN 16524, in order to exclude a change of colour.

- We recommend to omit adhesive straps.
- Using non-absorbent substrates and / or slowly absorbent printing inks, we recommend to plan for the corresponding drying times.
- There must be a suitability for water-based coating if anti-set-off powder is used (do not use mineral powder).
- Recommended pile temperature: not > 35°C
- There must be a sufficient hardening of the overall system substrate-printing ink-coating before further processing which should be checked in the process.
- The full profile of characteristics of the coating film is available after complete drying.
- For the further processing of the sheets under mechanical load and/or the influence of humidity, a sufficient high basic consistency of the substrate is required.
- The coating is suitable for wrapping in foils XS and MS (no acrylic coated foil).
- In order to guarantee a fast and complete drying, we recommend a sufficient airing of the sheets.

Cleaning instructions

- Please clean machines and tools immediately with water. Dried coating residues can be removed with TERRAWET Clean Cleaning Agent G 12/180.

Storage instructions

- Shelf-life 18 months

- Applies to closed original containers at 5°C up to 30°C.
- Avoid mixing with other coatings or washing water.
- Protect from frost, heat and sun exposure.
- Storage may cause a change in viscosity. We recommend to check the viscosity and adjust - if necessary - with water.

Disclaimer

- All information provided on this product (in this sheet or elsewhere) are made to the best of our knowledge.
- All information are technical quality descriptions, advisory and due to the wide range of materials, production conditions, operations and processes they do not release from own tests and examinations under customer-specific circumstances.
- If an application is intended to be made under different conditions than those specified in this sheet, we only assume liability after having examined the respective different conditions.
- This data sheet does not claim to be complete.
- We reserve the right to change product characteristics due to technical progress, amendment of applicable law and mandatory production-related needs.